

DYM-710L

Wire & Cable Compound

Semiconductive Jacketing Compound

Description

DYM-710L is a thermoplastic semiconductive jacketing compound for power cables based on LLDPE. This product gives the excellent physical, electrical properties and good processibility.

Specification

ICEA S-94-649 / AEIC CS8 / IEC 60502-2, 60840, 62067 ST7

Typical Physical-Electrical Properties

Test Items	Test Method	Unit	Value
Density at 23°C	ASTM D 792	g/cm ³	1.06
Tensile Strength(25 mm/min)	IEC 60811-501	N/mm ²	20
Elongation at break	IEC 60811-501	%	600
Tensile Strength after 168hrs at 100°C	IEC 60811-401	%	> 80
Retention			
Elongation at break after 168hrs at 100°C	IEC 60811-401	%	> 80
Retention			
Tensile Strength after 168hrs at 121°C	IEC 60811-401	%	> 80
Retention			
Elongation at break after 168hrs at 121°C	IEC 60811-401	%	> 80
Retention			
Volume Resistivity			
at. 23 °C	ASTM D 991	Ω·cm	< 50
at. 90 °C	ASTM D 991	Ω·cm	< 50
E.S.C.R (50°C, Igepal 10%, F0)	ASTM D 1693	hrs	> 2000
Moisture Content	Karl Fischer-titration	ppm	< 800
Heat Deformation 121°C, 2kg	JIS C 3005	%	< 10
Weather test(2000hrs)	Weather-O-Meter	-	No crack
Brittleness temperature at -60°C	ASTM D 746	-	No fracture
Hardness (Shore D)	ASTM D 2240	-	60

* E.S.C.R : Environmental stress cracking resistance

* Data should not be used for specification work.

Processing Techniques

Recommending standard extrusion temperature profiles of **DYM-710L** are as follows

Unit: °C

Zone 1	Zone 2	Zone 3	Zone 4	Zone 5	Adapter	Head	Die
150±5	155±5	160±5	165±5	170±5	170±5	170±5	170±5

It is recommended that this product can be used conventional PE/PVC extruder. (L/D is 25~22/1 and C/R is 1.8~2.5:1) Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. We recommend hopper drying at 40~60°C for 4 hours to remove moisture before extrusion.

Packing

Form : 500kg Cardboard Box(Inner PE bag packing)

Handling

To ensure health and safety, Material Safety Data Sheets(MSDS) is available on request.

Storage

Should be stored at room temperatures between 10~50°C. Recommended maximum storage period in dry and clean place is 12months unopened and in original packaging after the manufacture.

Disclaimer

The product can be used only for the application as specified here above. It is the customer responsibility to inspect and test our products to satisfy the suitability of this product to customer's particular purpose. No liability can be accepted regarding the use of our products in conjunction with other materials. No warranties shall be offered which extend beyond the description contained here above. The above-mentioned information relates exclusively to our products when not used in conjunction with any third party materials.



A member of the
Borealis Group

DYM SOLUTION CO., LTD.

Head Office : 50, 2gongdan 8-gil, Seobuk-gu, Cheonan-si, Chungcheongnam-do, Korea, <http://www.dymsolution.co.kr>
Tel : +82(0)41 621 6250, 621 8421 Fax : +82(0)41 621 8420

Created Date: July, 2024 DYM-710L

Sensitivity: External